

BBBF

testing

DEVELOPED IN-HOUSE METHOD

SOP 33: BASED ON EN 12467:2012
+ A2:2018 SECTION 7.4.1.

CLIMATIC PERFORMANCE – FREEZE - THAW

Publication date: August 2023

Document reference: QMSD-SOP 33

Version: 04

Status: Issued



Copyright Notice

This testing standard is Copyright ©BBF TESTING 2022 and protected under UK and international laws.

This testing standard may be used and reproduced for the purpose of instruction and reference, subject to the following conditions:

- You must only use or reproduce this testing standard in connection with GRC products, including when purchasing, using, and specifying GRC products.
- You must not use or reproduce this testing standard for any other commercial purpose, including as supporting content for any other commercial products.
- You may not modify, alter, transform, build upon or create derivative works based upon this testing standard; and
- This notice must appear on all complete or partial copies of this standard which you create.

SECTION 1: FORWARD

This testing procedure is based on EN 12467:2012 + A2:2018 Section 7.41.

It has been developed in modified form to provide a test for determining the effect of a cycle of freezing and thawing on Glassfibre Reinforced Concrete (GRC) to determine loss of flexural strength at both the elastic/yield (LOP) and ultimate (MOR) levels.

The test method follows the requirements of the EN standard test with the following errors, omissions, modifications, or deviations.

- 1.1. The 3-point bending test described in Section 7.3.2 of the standard is substituted for the 4-point bending test as detailed in EN 1170-5:1998.

This test is deemed more suitable for Glassfibre Reinforced Concrete.

- 1.2. Specimen sizes and sampling are in accordance with EN 1170-8:2008

SECTION 2: REFERENCES

The following published standards are required for the application of this test method:

EN 1170-5:1998 Measuring bending strength 'Complete bending test' method.

EN 1170-8:2008 Test method for glass fibre reinforced cement Part 8 Cyclic weathering type test.

EN 12467:2012 Fibre cement flat sheets – Product Specification and test methods.

SECTION 3: APPARATUS

- 3.1.: A freezer meeting the requirements detailed in EN 12467:2012 Section 7.4.1.2.1
- 3.2.: A temperature control water bath meeting the requirements of EN 12467:2012 Section 7.4.1.2.2.
- 3.3.: A 4 Point Bending Test Machine meeting the requirements of EN 1170-5:1998 Section 4.

SECTION 4: PROCEEDURE

- 4.1.: A test board allowing sampling as detailed in Figure 1 of EN 1170-8:2008 is to be manufactured using the same production methodology as that used to manufacture GRC products.
- 4.2.: The board is to be removed from the mould after a minimum of 12 hours but not exceeding 24 hours.
- 4.3.: The board is to be stored in the production facility until 6 days old.
- 4.4.: Specimens are to be cut from the board using a suitable masonry saw.

The length, width and thickness of the specimens is to be in accordance with EN 1170-5:1998 but not exceed a thickness of 12.5 mm.

Cut specimens are to be packed in airtight plastic bags for transportation to the testing laboratory.

The transportation time from the manufacturing location to the testing laboratory is to be disregarded in respect of determining specimen age.

- 4.5.: On receipt of the specimens at the testing laboratory they are to be removed from the sealed bags and placed in a humidity chamber at 20°C (± 3°C) 60% (± 5%) relative humidity for 21 days.
- 4.6.: At 27 days old the 8 "R" specimens are to be immersed in water at a temperature of 20°C (± 2°C) for 24 hours.
- 4.7.: Carry out the Full Bending Test as detailed in 1170-5 within 30 minutes of removing specimens from water and wiping with a damp cloth to remove surface water.
- 4.8.: At 27 days old the "C" specimens are to be immersed in water at a temperature of 20°C (± 2°C) for 48 hours.
- 4.9.: After removal the 8 "C" specimens are to be subjected to 25 freeze-thaw cycles as detailed in EN 12467:2012 Section 7.4.1.3.

4.10.: On completion of the 25 cycles carry out the Full Bending Test as detailed in 1170-5:1998 within 30 minutes of removing specimens from water and wiping with a damp cloth to remove surface water.

SECTION 5: RESULTS

Pair each of the 8 “R” & “C” specimens and designate as i ($i = 1-8$) and calculate the individual ratios as detailed in EN 12467:2012 Section 7.4.1.4 noting ratios should be calculated for both Limit of Proportionality and Modulus of Rupture.

Calculate RL of the mean of ratios for LOP and MOR as detailed in EN 12467.